

Proofings Coated Fabrics Ltd

Hare Hill Road
 Littleborough
 Lancashire OL15 9HE
 Telephone +44 (0)1706 372314
 Fax +44 (0)1706 370473

DATA SHEET

SPECIFICATION No: 3339

DESCRIPTION	POLYMER COATING	BASE FABRIC TYPE	TYPICAL APPLICATIONS
D/F RED/BLACK IIR PLIED P/AMIDE 1500mm VULCANISED	ISOPRENE / ISOBUTYLENE RUBBER	PLY-1 RED POLYAMIDE PLY-2 BLACK TIRESSA POLYAMIDE	DRY-SUITS

PHYSICAL PROPERTIES

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>RESULT</u>
BASE FABRIC MASS	BSF 100 METHOD 18	PLY-1 60g/m2 NOMINAL PLY-2 80g/m2 NOMINAL
COATING MASS	BSF 100 METHOD 18	145g/m2 NOMINAL
OVERALL MASS	BSF 100 METHOD 18	285 +/- 25g/m2
WIDTH	BSF 100	1600mm NOMINAL
AIR POROSITY	BSF 100	NO LEAKS 10 MINUTES @ 4Psi
STATE OF CURE	BSF 100	VULCANISED

TECHNICAL DATA SHEETS

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product within the scope of technical progress or developments. The recommendations made in this leaflet should be checked to preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.

Elastomeric, Rubber Coated Textiles and Foil Laminates

Registered No. 785832 England

VAT No 124756216