



# V-TEK TP7 TRILAMINATE

Categorie: Workshops. Tags Prodotto: triapoly-7 and trilaminati.

- V-Tek (60,5% nylon + 20% polyester + 12% kevlar® + 7,5% PU)
- Butyl
- Polipro polyester 75D

**Available colors:** Black/gray

ITEM	METHOD	RESULT		REMARK	
		WARP /	WEFT	WARP /	WEFT
Weight (g/m <sup>2</sup> )	BS 6F 100	536		505~555	
Width (cm)	BS 6F 100	145.9		142.2	
Thickness (mm)	BS 6F 100	0.66		0.63~0.69	
Tensile strength (N/5cm)	BS 6F 100	1902.5 / 1071.1		1800 / 900 ↑	
Elongation (%)	BS 6F 100	32 / 28		35/30 ↓	
Tongue Tear strength (N)	BS3424 PART5 METHOD 7B	455 /427		400 / 390 ↑	
Ply-Adhesion (N/5cm)	BS 6F 100	55/ 57		50/50 ↑	
耐水壓 Resistance to water penetration (mmH <sub>2</sub> O)	JIS L 1092 Hydrostatic	15000 ↑		15000 ↑	
Air Porosity	BS 6F 100	None bubbles		None bubbles	